

TECHNICAL INFORMATION DYNACOAT 1K PLASTICS PRIMER (AEROSOL) — D2.01.05a UK & Ireland

Quick drying, one-pack adhesion primer for plastic car body parts.



Shake thoroughly before use



APPLICATION DISTANCE 12-18 cm







Invert aerosol and depress nozzle after use



RECOATABILITY

Recoatable after 20 minutes at 20°C Recoat within 24 hours at 20°C



RECOATABLE WITH

All Dynacoat fillers, basecoats and topcoats



PROTECTION

Use suitable respiratory protection. AkzoNobel Vehicle Refinishes recommends the use of a fresh air supply respirator.



TECHNICAL INFORMATION DYNACOAT 1K PLASTICS PRIMER (AEROSOL) — D2.01.05a UK & Ireland

Dynacoat 1K Plastics Primer: Polyolefin resins All plastic car body parts currently available in the automotive industry except for those made of pure PE (polyethylene)
All plastic car body parts currently available in the automotive industry except for those
Note: Do not apply 1K Plastics Primer to plastic parts that are already pre-treated with OEM primer
Pre-clean the surface with warm water and detergent and rinse sufficiently with clean water. Remove surface contamination with Uni-degreaser
Apply 1 single coat, allowing for 20 minutes flash off time before applying Dynacoat fillers / topcoats.
To clean spray can opening, invert aerosol to allow propellant to clear nozzle
1-4 μm
Allow for a minimum of 20 minutes flash-off time at 20°C before recoating. Apply filler or topcoat within 24 hours at 20°C
Dynacoat fillers, basecoats and topcoats
Aerosol
1 year at 20°C
2004/42/IIb(e)(840)780 The EU limit value for this product (product category: IIb(e)) in ready to use form is 840 gram/liter of VOC. The VOC content of this product in ready to use form is max. 780 gram/liter.



TECHNICAL INFORMATION DYNACOAT 1K ETCH PRIMER (AEROSOL) — D2.03.01

Akzo Nobel Coatings LTD Address: Unit 2B, Didcot Park
Churchward, Southmead Industrial Estate
Didcot, Oxfordshire, OX11 7HB

Tel: +44 (0)1235 862226

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel. Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3, 2170 BA Sassenheim, The Netherlands. www.dynacoat.com